



2V805AH



Features:

- ▲ Maintenance-free operation
- ▲ Stable quality and high reliability
- ▲ Compact design
- ▲ 12 years design time (at 25°C)

Applications:

- ♣ UPS (Uninterruptable Power System)
- ♣ Emergency lighting
- ♣ Solar panel system
- ♣ Alarm and security system
- ♣ Tele-communication system
- ♣ Fire alarm and security systems
- ♣ DC power supply Auto control system
- ♣ Backup power for testing and measuring instruments
- ♣ Electronic apparatus and equipment Communication power supply
- ♣ etc

Specifications:

Type	Specification
Nominal Voltage	2v
Nominal Capacity	805ah
Dimension	Length: 410±3mm
	Width: 175±3mm
	Container Height: 330±3mm
	Total Height(with Terminal):350±3mm
Approx Weight	49.0kg
Terminal	T11
Container material	ABS
Rated Capacity	820.0ah/52.5A (20hrs, 1.80V/cell,25°C/77°F)
	805.0ah/100.0A (10hrs, 1.80V/cell,25°C/77°F)
	655.0ah/171.0A (5hrs, 1.75V/cell,25°C/77°F)
	550.0ah/250.0A (3hrs, 1.75V/cell,25°C/77°F)
	500.0ah/600.0A (1hrs, 1.60V/cell,25°C/77°F)
Max.Discharge Current	7000A(5s)
Internal Resistance	Approx 1.6mΩ
Operation Temp.Range	Discharge:-15-50°C(5-122°F)
	Charge: 0-40°C(32-104°F)
	Storage: -15-40°C(5-104°F)
Nominal Operating Temp.Range	25±3°C(77±5°F)
Cycle Use	2.4V-2.5V(25°C/77°F) Coefficient:30mv/°C (Initial charging current less than 300A)
Standby Use	2.25V-2.3V(25°C/77°F) Coefficient:20mv/°C (No limit on Initial Charging Current)
Capacity affected by Temp.	103% 40°C(104°F)
	100% 25°C(77°F)
	86% 0°C(32°F)

Self Discharge:

KANGLIDA batteries may be stored for up to 6months at 25°C (77°F) and then a freshing charge is required, for higher temperatures the time interval will be shorter.


Constant Current Discharge (Amperes) at 25 °C (77°F)															
F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	1166.7	1028.0	903.6	799.9	668.5	543.0	443.2	297.0	227.0	183.0	156.7	137.8	111.8	95.5	50.7
1.80V/cell	1420.0	1203.0	1029.7	896.6	734.5	583.9	472.1	312.5	246.0	189.3	163.0	143.7	117.1	100.0	52.5
1.75V/cell	1659.7	1378.5	1165.0	993.6	799.0	632.1	508.0	331.5	250.0	199.8	171.0	150.5	120.1	102.0	53.2
1.70V/cell	1899.3	1558.3	1287.6	1092.6	868.2	675.2	537.8	350.0	261.0	208.0	177.9	155.8	124.0	104.5	54.3
1.65V/cell	\	1666.0	1369.9	1154.9	909.7	701.8	558.8	361.5	269.3	214.3	182.8	158.7	126.3	106.2	55.2
1.60V/cell	\	1866.7	1539.9	1287.6	995.0	759.1	600.0	379.5	280.7	223.3	191.3	165.7	131.0	109.6	56.9

Constant Power Discharge (Watts) at 25 °C (77°F)															
F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	2144.9	1909.1	1695.1	1515.8	1280.8	1049.1	859.3	579.7	444.8	369.6	308.7	272.4	221.8	189.9	100.8
1.80V/cell	2582.9	2206.1	1905.9	1674.2	1385.9	1119.5	910.5	605.9	479.3	369.9	319.7	282.7	231.7	198.6	104.4
1.75V/cell	2954.9	2489.9	2129.9	1837.6	1495.2	1200.3	975.3	640.4	485.2	389.1	334.2	296.3	237.1	202.3	105.6
1.70V/cell	3288.3	2751.1	2321.5	2005.7	1615.7	1277.4	1029.2	674.7	505.6	404.4	347.2	305.3	244.5	207.1	107.8
1.65V/cell	\	2914.5	2451.1	2104.2	1679.2	1315.8	1061.8	692.9	519.5	415.0	355.5	309.9	248.3	210.2	109.4
1.60V/cell	\	3225.9	2709.8	2320.6	1823.9	1415.8	1134.0	723.9	538.9	431.1	370.8	322.6	257.2	216.5	112.6


Note: the above characteristics data are average values obtained within three charge/discharge cycles, not the minimum values.

Characteristics:


Discharge Characteristics




Float Charging Characteristics




Temperature Effects in Relation to Battery Capacity




Self Discharge Characteristics



Cycle Life in Relation to Depth of Discharge



Effect of Temperature on Long Term Float Life



Attentions:

1. After received product, please checked box damaged or not, if find crack on battery body, contact with us and logistics, it should be caused by boorish handle during delivery;
2. Don't pull or shake terminal, otherwise, it may cause terminal loosen;
3. Battery is not allowed close to Tepid source or basked under the sun for a long time;
4. Charge in the obturate container is not allowed;
5. No short circuit. Battery should be stored full of electronic when not in need, and the battery should be charged every three months in order to avoid the irreversible sulphation. When battery case bursts or electrolyte leaks, battery should be changed lest the acid corrosion.
6. No battery in environment with the acid gas.
7. When battery is used as the backup battery, be careful and check it at regular time to avoid the damage battery. Especially the battery beyond one year should be checked in time, and change the less capacity and scrapped battery. (some batteries maybe have voltage but no current; some batteries maybe have current but no voltage; some maybe have both but less capacity: all these conditions cannot meet the work, reach the power-on time. Do not forth small battery, cause the huge losses)
8. Forbidden put battery in the fire, otherwise it will cause an explosion.
9. When battery cracks or leaks, please use cotton cloth clean it. When skin contacts to the liquid, wash with fresh water immediately. See doctor if serious.
10. No wash on the surface of the battery with the organic solution.